



Fantastix series technical specifications

EVALUATED IN ACCORDANCE WITH ANSI STANDARD A137.1

TEST	DESCRIPTION	RESULT	STATUS
ASTM C373	Water Absorption	0.00%	Passes
ASTM C424	Crazing Resistance	No evidence of crazing	Passes
ASTM C482	Bond Strength	291 psi, average	Passes
ASTM C484	Thermal Shock Resistance	No evidence of visual defects	Passes
ASTM C1026	Freeze-Thaw Cycling	No visible evidence of damage	Passes
ASTM C1027	Abrasion Resistance	Class III	
ASTM C1028	Static Coefficient of Friction	DRY WET	
		0.95 0.61	